

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup>:</b> <b>A61L 29/00, C08J 7/04</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 94/16747</b> <b>(43) International Publication Date:</b> 4 August 1994 (04.08.94)
<b>(21) International Application Number:</b> PCT/DK94/00035 <b>(22) International Filing Date:</b> 20 January 1994 (20.01.94) <b>(30) Priority Data:</b> 0071/93 21 January 1993 (21.01.93) DK <b>(71) Applicant (for all designated States except US):</b> COLOPLAST A/S [DK/DK]; Egevangen 4, DK-2980 Kokkedal (DK). <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> RØDSTEN, Carsten, Bob [DK/DK]; Brandbjerggård, Sæby, DK-4070 Kirke Hyllinge (DK). <b>(74) Agents:</b> ROTNE, Jens, Styrup et al.; Internationalt Patent-Bureau, Høje Taastrup Boulevard 23, DK-2630 Taastrup (DK).		<b>(81) Designated States:</b> AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, HU, JP, KP, KR, KZ, LK, LU, LV, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SK, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>In English translation (filed in Danish).</i>
<b>(54) Title:</b> A METHOD FOR PRODUCING A HYDROPHILIC COATING ON A SURFACE AND A MEDICAL ARTICLE PRODUCED BY THE METHOD		
<b>(57) Abstract</b>  A hydrophilic coating with improved retention of water on a surface, especially a surface of a medical device such as a urethra catheter, prepared by applying on to the surface in one or more process steps at least one solution of components that will combine to form the hydrophilic coating. During the final process step, the surface is coated with an osmolality promoting agent, which is dissolved or emulgated in the solution or in the last solution to be applied, forming the hydrophilic coating.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

A METHOD FOR PRODUCING A HYDROPHILIC COATING ON A SURFACE  
AND A MEDICAL ARTICLE PRODUCED BY THE METHOD

This invention relates to a method of preparing a  
5 hydrophilic coating as described in the introductory part  
of claim 1.

It is known to coat medical devices, e.g., catheters  
for introduction into human cavities such as blood vessels,  
digestive organs and the urinary system, with a hydrophilic  
10 coating, as a minimum applied on that part of the surface  
which gets into contact with the mucous membranes, etc.,  
during introduction of the device. Whereas such coating in  
dry condition is not particularly smooth, so that the  
handling of the device does not become inconvenient, when  
15 it is moistened with water immediately before introduction  
into the human body it becomes extremely slippery, thereby  
providing a substantially painless introduction.

A large number of methods are known for the production  
of hydrophilic surface coatings.

20 These methods are mainly based on the fact that the  
substrate to be provided with a hydrophilic surface  
coating, in the course of one or more process stages with  
intermediary drying and curing, is coated with one or more  
(mostly two) layers, which are caused to react with one  
25 another in different ways, e.g., by polymerization  
initiated by irradiation, by graft polymerization, by the  
formation of interpolymeric network structures, or by  
direct chemical reactions. Regarding this subject, please  
refer to DK-A-900 855, DK-B-159 018, EP-A-379 156, EP-A-  
30 454 293, EP-B2-93 093, GB-A-1 600 963, US-A-4 119 094, US-  
A-4 373 009, US-A-4 729 914, US-A-5 041 100, and US-A-  
5 120 816, and to WO-A-9005162 and WO-A-9119756.

According to a method known from US-A-5 001 009, a  
hydrophilic surface coating is prepared on a substrate by  
35 applying, in two stages or in one combined stage, on the  
substrate a reactive or an adhesive primer layer and then  
the actual hydrophilic surface layer, which in this case

comprises polyvinylpyrrolidone [PVP] as the active constituent. By this method, there is no chemical reaction between the components of the two layers applied.

Where a device of said type, e.g., a catheter, is to remain inside the body only for a short period, there may be a risk that water will be extracted from the hydrophilic surface coating and into the body fluids in the surrounding mucous membranes etc., owing to the higher osmotic potential of said body fluids. As a result of the extraction of water, the hydrophilic surface coating will have a tendency to stick to the surrounding tissues, and the removal of the medical device from the body may be painful.

EP-B-217 771 describes a method of said type for the production of an improved hydrophilic coating that maintains the smoothness of the coating for a longer period of time.

According to this method, on a hydrophilic coating prepared by an already known technique and cured in a separate process stage, an additional and separate coating is applied, consisting of a solution including an osmolality promoting agent and selected from among mono- and disaccharides, sugar alcohols, and nontoxic organic and inorganic salts, whereupon the solvent is allowed to evaporate. As a viscosity controlling agent the solution may also contain a polymer. When dried outside the human body a surface produced according to this method remains moist in a longer period of time than conventionally prepared hydrophilic surface coatings, and catheters with a hydrophilic coating improved in this way will be easier to remove than those with a conventional coating.

As distinct from said method, the method according to the present invention is characterized by the measures stated in the characterizing part of claim 1.

The method according to this invention leads to a simpler production and an improved stability as compared to the known method according to EP-B-217771, since the

osmolality promoting agent, without any use of an additional, separate coating step, is included in that solution from which the hydrophilic surface coating or its outermost layer is produced. The osmolality promoting agent  
5 is most frequently dissolved in the same solvent as the components for producing the hydrophilic coating, but may also merely be emulgated or suspended therein.

In the method of the invention the osmolality promoting agent may be any compound that ensures the  
10 desired equalization of the difference in osmotic pressures between the moistened coating and the surrounding body fluid. It may thus be selected from among osmolality increasing electrolytes, e.g., of the same kind as described in said EP-B-217771, namely mono- and  
15 disaccharides, sugar alcohols, and nontoxic organic or inorganic salts, which may be soluble or insoluble in the solution into which the agent is incorporated. In the method according to the invention, however, the osmolality promoting agent is preferably selected from among urea,  
20 amino acids, organic and inorganic acids, and polypeptides and/or mixtures hereof, said agent being preferably incorporated into the solution by dissolution or emulsification.

The term "urea" used herein should be understood to  
25 comprise urea that has been N-substituted or N,N-disubstituted by lower alkyl.

The preferred embodiment of the method according to the invention in principle relies on process stages corresponding to those described in said US-A-5 001 009,  
30 where a primer is first applied to the substrate, for instance a primer containing nitrocellulose applied in a solution. After drying of the primer layer, an outer layer is applied consisting of a solution of polyvinylpyrrolidone in a solvent selected from among tetrahydrofuran,  
35 methyl(ene) chloride, toluene, acetone, a lower aliphatic alcohol, cyclohexanone, C<sub>2</sub>-C<sub>4</sub>-alkyl acetates, butyrolactone, and dimethylformamide, the most important

constituent being ethyl alcohol. According to the invention, this solution contains urea as the osmolality promoting agent in a quantity of 1-20 per cent by weight, preferably 2-15 per cent by weight and particularly 3-8 per cent by weight on the basis of dry polyvinylpyrrolidone.

If said content of urea exceeds a value of about 10 per cent by weight, on the basis of dry polyvinylpyrrolidone, a smarting sensation may be felt at the introduction of the catheter, depending on the nature of the hydrophilic coating.

As explained in the following, testing achieved good results with a urea quantity of 5-6 per cent by weight. It was found that a significantly lower amount of urea does not give the desired effect with regard to retention of the water used to moisten the coating before introduction of the device, whereas a significantly larger amount may cause inconveniences in the form of a smarting sensation during the introduction.

The invention also relates to a medical device for introduction into a body cavity, as described in the introductory part of claim 5.

Such devices may especially include catheters, wound drains, and certain surgical instruments. Regardless of the fact that the primary object of this invention is the production of improved catheters for introduction into the urethra in connection with the treatment of dysuria and the achievement of bladder control, the invention embraces all such devices intended for the introduction into and withdrawal from a body cavity, whether for human or veterinary use.

A medical device of said type is, according to the invention, characterized in the features stated in the characterizing part of claim 5.

The example below illustrates the preparation according to the invention of a hydrophilic coating on a catheter based on a polyvinyl chloride [PVC] substrate as well as a test of the coated catheters prepared this way

with different contents of urea as the osmolality promoting agent, illustrating the improved retention of water on such produced hydrophilic surfaces.

5

## E X A M P L E

A catheter made of PVC was prepared according to a modification of the method described in Example 1 in US-A-5 001 009 and coated on part of its surface with a hydrophilic coating with improved water retention by first applying  
10 a primer layer by immersion into a mixture of 5.4 g of low-viscosity nitrocellulose, 2 g of dibutylphthalate, and 1.9 g of polyvinyl butyral [PVB], in a mixed solvent comprising isopropanol, ethyl acetate, ethanol, and acetone  
15 (36:13:6:25:18:1.5 vol/vol). After drying for 5 minutes at 65°C, the catheter coated as described above was provided with an outer layer by immersion into a solution of 6.6 g of polyvinylpyrrolidone and 5 per cent by weight of urea in relation to polyvinylpyrrolidone in a solvent mixture of  
20 ethanol, ethyl acetate, and dimethylformamide (64:23.5:12.5). Finally, the catheter was dried at 65°C for 60 minutes.

Three healthy volunteers (A, B, and C) assessed the resistance when a catheter prepared according to said  
25 method was removed after a conventional catheterization, according to the following score system:

- |    |                    |
|----|--------------------|
| 1  | No resistance      |
| 2  | Slight resistance  |
| 30 | 3 Great resistance |

The table below shows the results:

T A B L E

Volunteer		Urea content, per cent by weight			
5		6	4	3	0
	A	1	1	3	3
	B	1	1	1	1
	C	1	2	3	3



## P A T E N T   C L A I M S

1. A method for the preparation of a hydrophilic coating with improved retention of water on a surface, wherein the surface, in one or more process steps, is coated with at least one solution of agents, which agents will combine to form such a hydrophilic coating, and wherein in the final process step an osmolality promoting agent is applied to the surface, characterized in that the osmolality promoting agent is incorporated into said solution or into the last solution applied of several such solutions and applied in the same process step as this solution.

2. A method according to claim 1, characterized in that the osmolality promoting agent is selected from among osmolality increasing electro-lytes.

3. A method according to claim 1, characterized in that the osmolality promoting agent is selected from among urea, amino acids, organic and inorganic acids, and polypeptides and mixtures thereof, and incorporated into said solution by dissolution or emulsification therein.

4. A method according to claim 3, where said solution comprises polyvinylpyrrolidone or a derivative thereof as the active component, characterized in that the osmolality promoting agent in the solution comprises urea in a quantity of 1-20 per cent by weight, preferably 2-15 per cent by weight and particularly 3-8 per cent by weight, based on the quantity of dry polyvinylpyrrolidone.

5. A medical device for introduction into a body cavity, which device on at least part of its surface has a hydrophilic coating, of which the water retention has been improved by means of an osmolality promoting agent, characterized in that said osmolality promoting agent is incorporated into the hydrophilic coating itself by incorporating the agent in a solution or

in the last solution applied from which the coating is formed.

6. A device according to claim 5, c h a r a c -  
t e r i z e d in that the osmolality promoting agent has  
5 been selected from among osmolality increasing electro-  
lytes.

7. A device according to claim 5, c h a r a c -  
t e r i z e d in that the osmolality promoting agent has  
been selected from among urea, amino acids and polypeptides  
10 and mixtures thereof.

8. A device according to claim 5 or 6, where the  
layer(s) of the coating include(s) polyvinylpyrrolidone or  
derivatives thereof, c h a r a c t e r i z e d in that  
the osmolality promoting agent comprises urea in a quantity  
15 of 1-20 per cent by weight, preferably 2-15 per cent by  
weight and particularly 3-8 per cent by weight, based on  
the quantity of dry polyvinylpyrrolidone in the outermost  
layer.

9. A device according to any one of the claims 5-8,  
20 c h a r a c t e r i z e d in that the medical device is  
a catheter, mainly intended for introduction into the  
urethra.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 94/00035

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC : A61L 29/00, C08J 7/04

According to International Patent Classification (IPC) or to both national classification and IPC

### B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC : A61L, C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPODOC, WPI CLAIMS, CA

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	DK, A, 9200768 (UNO PLAST A/S), 11 December 1993 (11.12.93)	1-3, 5-6, 9
	&	
	EP, A1, 0586324 (UNO PLAST A/S), 9 March 1994 (09.03.94)	
	--	
X	EP, A1, 0217771 (ASTRA MEDITEC AB), 8 April 1987 (08.04.87)	1-3, 5-6, 9
	--	
A	EP, A1, 0093093 (ASTRA MEDITEC AB), 2 November 1983 (02.11.83)	1-9
	-- -----	



Further documents are listed in the continuation of Box C.



**See patent family annex.**

- |     |   |     |  |
|-----|---|-----|--|
|     | Special categories of cited documents:  |     |  |
| "A" | document defining the general state of the art which is not considered to be of particular relevance  | "T" | later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  |
| "E" | earlier document but published on or after the international filing date  | "X" | document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone   |
| "L" | document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) | "Y" | document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art |
| "O" | document referring to an oral disclosure, use, exhibition or other means  | "&" | document member of the same patent family  |
| "P" | document published prior to the international filing date but later than the priority date claimed  |     |  |

Date of the actual completion of the international search

**2 May 1994**

Date of mailing of the international search report

05 -05- 1994

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

**Authorized officer**

**Sofia Nikolopoulou**  
Telephone No. +46 8 782 25 00

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

16/04/94

International application No.  
PCT/DK 94/00035

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
DK-A- 9200768	11/12/93	NONE	
EP-A1- 0586324	09/03/94	NONE	
EP-A1- 0217771	08/04/87	SE-T3- 0217771	
		AU-B- 591703	14/12/89
		AU-A- 6246486	02/04/87
		CA-A- 1292649	03/12/91
		DE-A- 3682742	16/01/92
		JP-A- 62082968	16/04/87
		US-A- 4906237	06/03/90
EP-A1- 0093093	02/11/83	SE-T3- 0093093	
		AU-B- 556351	30/10/86
		AU-A- 1326783	27/10/83
		CA-A- 1215597	23/12/86
		GB-A,B- 2122510	18/01/84
		JP-C- 1670911	12/06/92
		JP-B- 3035990	30/05/91
		JP-A- 58193767	11/11/83
		SE-B,C- 430695	05/12/83
		SE-A- 8202523	23/10/83
		US-A- 4585666	29/04/86
		US-A- 4666437	19/05/87